

#### **Reusche Colors**

## Decorator's Choice with Cadmium Option

#### **Profile:**

Glass enamels, exhibiting high gloss

#### **Firing Temperature:**

1120-1180°F (600-640C) Firing cycles are dependent on the type of thickness of the glass, type of lehr and belt speed.

### Mixibility:

All colors within the range are fully intermixable with the exception of cadmium bearing colors. However, we recommend running pre-production tests to verify color stability.

#### **Application:**

Supplied as powder or pastes for screen printing, either hot or cold, and spraying.

#### Health & Safety:

For detailed Health and Safety requirements consult the appropriate Material Safety Data Sheets.

(Pb)	Formulated without lead or cadmium (unless otherwise stated) using a zinc borosilicate frit. No lead was intentionally added to these colors.
	For use on cosmetic bottles, ad specialty items and non-returnable bottles

### **Reusche Colors**

# Decorator's Choice with Cadmium Option\*

Recommended Firing Temperature 1100-1180F

<b>Product Number</b>	Description	Color Swatch
RZ1000	Clear	N/A
RZ1001	White	N/A
RZ1002	Extreme White	N/A
RZ1003	Etch #1	N/A
RZ5004 *	Orange Red	
RZ5005 *	Orange	
RZ5003 *	Red	
RZ5006 *	Ruby Red	
RZ5001	Iron Red #1	
RZ5002	Iron Red #2	
RZ2001	Lemon Yellow	
RZ2002	Citrus Yellow	
RZ2004 *	Yellow	
RZ6004 *	Brown	
RZ6001	Autumn Brown	

### **Reusche Colors**

# Decorator's Choice with Cadmium Option\*

Recommended Firing Temperature 1100-1180F

<b>Product Number</b>	Description	Color Swatch
RZ3001	Green	
RZ4003	Baby Blue	
RZ3003	Chrome Green	
RZ3002	Turquoise	
RZ4001	Blue	
RZ2003	Metallic Gold	
RZ8001	Peach	
RZ6002	Rust Brown	
RZ6003	Chocolate Brown	
RZ7001	Black	