



**Schilling** inc.  
INKS & COATINGS

## WBC 3500 Hydrothane Frost Coatings for Glass

### TECHNICAL DATA SHEET

#### Product:

WBC 3500 is a decorative and protective coating for glass and ceramic based on urethane technology. WBC 3500 is available as a clear frost base which can be used as an acid etch imitation, tinted with Schilling's WBT Waterborne Tinters, or can be supplied fully formulated in any transparent or opaque color. WBC 3500 is suitable for decorative glassware, art deco tile, ceramic for bath and exterior decoration, sublimation base, cosmetics, and liquor and wine bottles requiring water immersion resistance. Notable features of this product include:

- Superior chemical and color bleed resistance, including against fragrances and lotions
- Resists plugging and is easy to clean with just water
- Proposition 65 compliant and BPA Free
- Suitable for water immersion
- Superior abrasion resistance in filling line applications and transit
- Compatible with Schilling UV cure inks for further decorating and overprint

#### Handling and Application:

Store in a cool dry place out of direct sunlight. Do not allow to freeze. Prior to application, mix well, but do not shake. Surfaces to be coated should be clean and dry. Flame treatment may optionally be used on surfaces prior to application, and coating may optionally be flame treated after curing for enhanced inter-coat adhesion between ink and coating film.

Cure Schedule	Flash off then 300-380 for 10-30 minutes convection, 3-5 minutes infrared. Cure schedule may vary with color, glass thickness, coating application thickness, and specific line configuration.
Application	Spray, Air Atomized or HVLP
Reduction	Pure Water
Viscosity @77F	25" #4 Ford—Other viscosities available upon request
Substrate	Clean Glass or Ceramic
Film Thickness	0.4-0.7 mil DFT
Coverage	640 square feet per gallon at 0.5 mil DFT
Clean Up	Water Clean Up. Glycol Ether EB or other organic solvents may also be used on dry residue.

#### Physical Properties

Density	8.5-10.0 lb/gal. Density varies with color.
Solids	20-25% volume solids. 22-27% weight solids. Solids content varies with color.
VOC and HAPS	1.1 lbs/gal as supplied. 3.2 lbs/gal minus exempt. HAPS Free.

Because Schilling Inc. cannot anticipate or control the many different conditions under which our products may be used or variations in customer handling or application, Schilling Inc. does not guarantee the suitability of our products and their use in any given situation. Users of our products should conduct their own tests to determine the suitability of any application. In the event the products sold are not fit or suitable for customer's intended use, seller's only obligation shall be to replace such quantity of the products proven to be defective. Seller shall not be liable for any injury, loss or damage, direct, incidental or consequential, arising out of the use or inability to use the products, and therefore, the products sold are sold without warranty express or implied. Customer acknowledges that customer is solely responsible for disposal of any unused product and containers.

TR05122023 FORM 2915CL0002