










# TECHNICAL INFORMATION

Tile collection performance and application recommendations

## TECHNICAL INFORMATION

	WATER ABSORPTION	ANSI / ISO - (%)	≤ 0.5		
	DEEP/ ABRASION RESISTANCE	ANSI / ISO - (PEI)	GLOSSY N/A	MATTE N/A	
			UNGLAZED 202 mm <sup>3</sup>		
	SCRATCH HARDNESS	ANSI / ISO - (Mohs)	6		
	BREAKING STRENGTH	ANSI - (lbf)	> 275		
		ISO - (N)	> 1220		
	SHADE VARIATION		V1		
	SLIP RESISTANCE	ANSI - DCOF (WET)	GLOSSY < 0.42	MATTE < 0.42	UNGLAZED > 0.65
		ISO - R VALUE	GLOSSY R (-)	MATTE R (-)	UNGLAZED R10
	CHEMICAL RESISTANCE	ANSI / ISO	CLASS A		
	STAIN RESISTANCE	ANSI ISO	CLASS A CLASS 5		
	FROST RESISTANCE	ANSI / ISO	PASS		

TEST VALUES ARE BASED ON ANSI / ISO STANDARDS ACCORDING TO: ANSI A137.1 - PORCELAIN TILE P1 CLASS, ISO 13006 - G - B1a GROUP, EN 14411 - G - B1a GROUP. VARIANCES IN TEST VALUES CAN OCCUR IN DIFFERENT PRODUCTION LOTS.

## USAGE RECOMMENDATIONS\*

		GLOSSY GLAZED PORCELAIN		MATTE GLAZED PORCELAIN		MATTE UNGLAZED PORCELAIN	
APPLICATION		WALL	FLOOR	WALL	FLOOR	WALL	FLOOR
INTERIOR	RESIDENTIAL	✓	✓	✓	✓	✓	✓
	COMMERCIAL	✓	✓	✓	✓	✓	✓
	HEAVY COMMERCIAL	✓		✓		✓	
EXTERIOR	RESIDENTIAL / COMMERCIAL	✓		✓		✓	✓

\* THESE ARE ANATOLIA RECOMMENDATIONS FOR SUITABLE APPLICATIONS. THEY ARE NOT DEFINED BY ANSI / ISO STANDARDS.

PLEASE NOTE THAT THE GLOSSY BEVELED ARABESQUE MOSAIC AND THE GLOSSY SCALLOP MOSAIC ARE ONLY RECOMMENDED TO BE USED ON THE WALL.