

ENGLISH BAY PHYSICAL PROPERTIES

GLAZED PORCELAIN		ENGLISH BAY VALUES	
Variation		V1	
Coefficient of Friction (COF)		0.69 wet, 0.88 dry	
Water Absorption		0.07%	
Frost Resistance		Frost Proof	
MOHS		7	
PEI		4	