

Dry - Pressed Ceramic Tiles ISO 13006 : 2012 Annex G - UNI EN 14411 : 2012 Annex G - Bla GL



CARATTERISTICHE TECNICHE Technical Features Caracteristiques Techniques Technische Eigenschaften Características Técnicas Технические Характеристики		NORMA Standard Norme Norm Norma Норма	VALORI Value Valeur Norme Vorgabe Valor Средние
	PLANARITÀ Flatness - Planéité - Ebenflächigkeit - Planiyud - Плоскостность	UNI EN ISO 10545/2	± 0,26% / ± 1,5mm
		ASTM C485 Warpage	
		Calibrated ± 0,75% (max ± 0,09 in)	-
		Rectified ± 0,40% (max ± 0,05 in-size ≤ 60cm) (max ± 0,07 in-size > 60cm)	± 0,25% (max ± 0,05 in-size ≤ 60cm) (max ± 0,07 in-size > 60cm)
	ASSORBIMENTO D'ACQUA - Valore medio in % Water absorption - Average value expressed in % Absorption d'eau - Valeur moyenne en % Wasseraufnahme - Durchschnittswert in % Absorción de agua - Valor medio en % - Поглощение воды	UNI EN ISO 10545/3 ≤ 0,5 % ASTM C373	Conforme Compliant
	RESISTENZA ALLA FLESSIONE Modulus of rupture - Resistance a la flexion Biegefestigkeit - Resistencia a la flexion - Прочность на изгиб FORZA DI ROTTURA Breaking strength - Résistance à la rupture Bruchlast - Resistencia a la rotura - Разрывное усилие	UNI EN ISO 10545/4	≥ 50 N/mm ²
		UNI EN ISO 10545/4 ASTM C648	≥ 2000 N 700 LBS
	RESISTENZA AL GELO Frost resistance - Résistance au gel - Frostbeständigkeit Resistencia a las heladas - Морозостойкость	UNI EN ISO 10545/12 ASTM C1026	Conforme Unaffected
	RESISTENZA CHIMICA ad alte e basse concentrazioni di acidi e basi Chemical resistance to high and low acid and basic concentrations Résistance chimique aux hautes et basses concentrations d'acides et de bases Chemikalienfestigkeit bei hohen und niedrigen Konzentrationen von Säuren und Basen Resistencia química con concentraciones altas y bajas de ácidos y bases Химическая стойкость к высоким и низким концентрациям кислот и щелочей	UNI EN ISO 10545/14 ASTM C-650	GA - GLA - GHA Unaffected
	RESISTENZA ALLE MACCHIE Stain resistance - Résistance aux taches - Fleckenbeständigkeit Resistencia a las manchas - Стойкость к образованию пятен	UNI EN ISO 10545/13 CTI 81-7D	5 No Evident Variation
	COEFFICIENTE DI ATTRITO Slip resistance - Coefficient de glissement - Rutschfestigkeit Barfußbereich Coeficiente de atrito medio - Коэффициент трения	DIN 51130 DIN 51097 ANSI A 137.1 - 2012 DCOF (Section 9.6) B.C.R.A.	R10 B (A+B) Dry: 0,81* / Wet: 0,68* > 0,40

* Values obtained with certificate n° 3639/2012/I. Date 10/26/2012.

Per maggiori chiarimenti sui dati tecnici e sulla garanzia consultare il catalogo generale in vigore.
For further information on technical specifications, please consult our up-dated general catalogue.



DIGITAL
PRINTING
TECHNOLOGY



IMBALLI E PESI Packing and weight - Emballages et poids - Verpackung und gewicht - Embalajes y pesos - Упаковка и вес								
Articolo Item Reference Artikel Articulo Артикула	Formato Size Format Format Тamaño ФОРМАТ cm.	Spessore Thickness Epaisseur Stärke Espesor ТОЛЩИНА mm.	Pz. x Scat. Pieces x Box Pcs / Bte Stk. x Krt. Pzs x Caja ШТ. x КОР.	Mq. x Scat. Sqm x Box Qm x Krt. M ² / Bte Mc. x Caja КВ.М. x КОР.	Peso x Scat. Weight x Box Gewicht x Krt.(kg) Poids / Bte(kg) Peso x Caja(kg) ВЕС x КОР. KG	Scat. x Pal. Boxes x Pal. Bte / Pal. Krt. x Pal. Cajas x Pal. КОР. x ПОДД.	Mq. x Pal. Sqm x Pal. Qm x Pal. M ² / Pal. Mc. x Pal. КВ.М x ПОДД.	Peso x Pal. Weight x Pal. Gewicht x Pal.(kg) Poids / Pal.(kg) Peso x Pal.(kg) ВЕС x ПОДД. KG
80K4_R	80x80	10,5	2	1,28	32,00	40	51,20	1280
60K4_R	60x60	10,5	3	1,08	25,00	36	38,88	900
63K4_R	30x60	10,5	6	1,08	25,00	40	43,20	1000
54K6_R	20x120	10,5	4	0,96	23,50	33	31,68	776
53K5_R 53K6_R	15x120	10,5	6	1,08	22,40	28	30,24	627
M30K4_	30x30	10,5	5	0,45	10,50	-	-	-

PROVENZA
a brand of EMILCERAMICA S.p.A.

